

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
24 February 2005 (24.02.2005)

PCT

(10) International Publication Number
WO 2005/016256 A2

- (51) International Patent Classification⁷: **A61K**
- (21) International Application Number:
PCT/US2004/023765
- (22) International Filing Date: 23 July 2004 (23.07.2004)
- (25) Filing Language: English
- (26) Publication Language: English
- (30) Priority Data:
60/493,116 7 August 2003 (07.08.2003) US
- (71) Applicant (for all designated States except US):
ETHICON, INC. [US/US]; U.S. Route #22, Somerville,
NJ 08876-1515 (US).
- (71) Applicants and
- (72) Inventors: **PENDHARKAR, Sanyog, M.** [US/US]; 9
Larch Drive, Old Bridge, NJ 08857 (US). **GORMAN,**
Anne, J. [US/US]; 314 Stockton Street, Hightstown, NJ
08520 (US).
- (74) Agents: **JOHNSON, Phillip et al.**; Johnson & Johnson
Corporate, One Johnson & Johnson Plaza, New Brunswick,
NJ 08933-7003 (US).
- (81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,
AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.
- (84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).
- Published:
— without international search report and to be republished
upon receipt of that report
- For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: HEMOSTATIC COMPOSITIONS CONTAINING STERILE THROMBIN

(57) Abstract: The present invention includes sterilized hemostatic compositions that contain a continuous, biocompatible liquid phase having a solid phase of particles of a biocompatible polymer suitable for use in hemostasis and that is substantially insoluble in the liquid phase, and sterile thrombin, each of which is substantially homogeneously dispersed throughout the continuous liquid phase, and methods for making such compositions.



WO 2005/016256 A2

HEMOSTATIC COMPOSITIONS CONTAINING STERILE THROMBIN

FIELD OF THE INVENTION

5 The present invention relates to hemostatic compositions containing sterile thrombin and to methods of making such hemostatic compositions.

BACKGROUND OF THE INVENTION

 Gelatin-based hemostats, both in solid sponge or powder form, are
10 commercially available and are used in surgical procedures. Gelatin powder, when mixed with fluid, can be prepared in various forms depending on the contemplated end-use and the ratio of fluid to powder. For example, where higher concentrations of fluid are employed, a paste or slurry that is useful as a flowable, extrudable and injectable hemostat may be prepared for use in diffuse bleeding, particularly from uneven surfaces
15 or hard to reach areas. Such conventional slurries are prepared at the point of use by mechanical agitation and mixing of the powder and liquid to provide uniformity of the composition. The paste then is placed into a delivery means or applicator, e.g. a syringe, and applied to the wound. In other cases, moldable compositions may be prepared with lower amounts of fluid and molded or packed to form a dressing for use
20 on external wounds. Gelatin powders are sterilized prior to preparing such compositions but mixing of the powders and fluids may compromise the sterility of the hemostatic composition due to handling of the materials at the site of use, or in general by exposure to the environment for relatively extended periods of time during mixing and the like.

25 Thrombin that is not terminally sterilized is known to be used in combination with such hemostatic compositions. Proteins such as thrombin are prepared aseptically and thus there is a risk that nonsterilized proteins such as thrombin, when used in hemostatic compositions, may compromise the sterility of the previously-sterilized materials, such as sterilized gelatin powder. However, as thrombin is known to be
30 denatured by exposure to sterilizing condition such as ionizing radiation conventionally used to sterilize the powders, which denaturing destroys all enzymatic activity of the thrombin, thrombin has not been reported to be incorporated into the hemostatic

compositions and then terminally sterilized prior to use to ensure a sterile composition. In fact, when thrombin is used in conventional hemostatic compositions, nonsterilized thrombin is added after sterilization of hemostatic composition.

It would be desirable if a sterile hemostatic composition containing active sterile
5 thrombin was available to the surgeon at the point of use without need for preparation, e.g. without having to add thrombin prior to use. The compositions of the present invention fulfill that need.

SUMMARY OF THE INVENTION

10 The present invention is directed to sterilized hemostatic compositions comprising a continuous, biocompatible liquid phase, a solid phase comprising porous or non-porous particles of a biocompatible polymer suitable for use in hemostasis and which are substantially insoluble in the liquid phase, and sterile thrombin. The continuous liquid phase comprises the solid particulate phase and sterile thrombin
15 substantially homogenously dispersed there through. The ratio of the liquid phase, the solid particulate phase and thrombin is effective to provide the composition with hemostatic properties, both prior to and after sterilization. Sterile compositions of the present invention may be prepared well in advance of the time of use while maintaining thrombin enzymatic activity even after being subjected to sterilizing radiation. The
20 present invention also includes methods of making the hemostatic compositions .

DETAILED DESCRIPTION OF THE INVENTION

Sterilized compositions of the present invention contain solid, porous or non-porous particles of a biocompatible polymer suitable for use in hemostasis, a
25 biocompatible liquid and sterile thrombin as its three primary components. Particles, liquid and thrombin are combined and mixed under conditions effective to provide a substantially homogeneous hemostatic composition comprising a continuous liquid phase comprising the thrombin and having the solid polymer particles homogenously dispersed there through. The amount and average diameter of particles contained in the
30 composition and the relative amounts of the solid, liquid and thrombin is effective to provide the composition with hemostatic and physical properties, as described herein below.

Compositions of the present invention may be prepared and sterilized by ionizing irradiation well in advance of the time of their intended use, while maintaining thrombin enzymatic activity effective to improve hemostasis of the composition when compared to a similar composition containing no thrombin or where the thrombin activity has been substantially diminished such that it no longer enhances hemostasis. This is particularly surprising given that it is known in the art that thrombin is denatured when exposed to irradiation of the type used to sterilize conventional hemostatic compositions containing, for example, gelatin powder. Denaturing causes the thrombin to lose its enzymatic activity. The compositions further may include additives to facilitate the preparation of the composition, enhance physical and mechanical properties, enhance the hemostatic properties of the composition or provide antimicrobial properties.

As used herein, "continuous" and "discontinuous" are used in the ordinary meaning of those words in the context of standard nomenclature used to define and describe dispersions.

As used herein, "substantially homogenous" denotes that physical state of the compositions or pastes where the solid particles are uniformly dispersed throughout the continuous liquid phase such that the ratio of solid:liquid and the density of any portion or cross-section of the composition or paste are substantially the same.

As used herein, "sterile" means substantially free of living germs and/or microorganisms and as further recognized and described by governmental standards pertaining to compositions and medical devices described and claimed herein.

As used herein, "hemostatic", or "hemostatic properties", means the ability to stop or minimize bleeding, as one skilled in the art of hemostasis would understand those terms to mean, as further exemplified in the examples of the specification.

A variety of biocompatible natural, semi-synthetic or synthetic polymers may be used to prepare the solid particles used in compositions of the present invention. The polymer selected must be substantially insoluble in the liquid chosen for the particular composition. Preferably, water-insoluble biodegradable polymers that provide mechanical, chemical and/or biological hemostatic activity are used. Polymers that may be used include, without limitation, proteins and polysaccharides. Polysaccharides that may be used include oxidized cellulose, chitosan, chitin, alginate, oxidized alginate and

oxidized starch. The biocompatible polymer used to prepare the particles preferably is a cross-linked or denatured protein, such as gelatin, collagen, fibrinogen or fibronectin. A preferred gelatin powder is a partially cross-linked gelatin powder prepared by milling gelatin sponge into particles having an average diameter of from about 40
5 microns to about 1200 microns, more preferably from about 100 microns to about 1000 microns, as determined by laser diffraction.

Sterile compositions of the present invention comprise a continuous liquid phase in which the sterile thrombin and solid particles are dispersed. Depending upon the particular medical device and use thereof, the liquid may be aqueous or non-
10 aqueous. Preferably, the liquid phase is aqueous. Aqueous liquids may include, without limitation, biocompatible aqueous solutions, such as calcium chloride and saline. More preferably, the liquid phase comprises saline. The liquid phase and solid particulate phase are present in relative amounts effective to provide a composition, for example a paste, or slurry, suitable for use in providing hemostasis. In certain embodiments, the
15 weight ratio of solid particles to liquid generally is from about 1:1 to about 1:12, or from about 1:3 to about 1:8 or even about 1:5.

Compositions of the present invention include compositions described herein that are sterile, in that they have been irradiated with a level of, e.g. ionizing irradiation. Such irradiation may include e-beam or gamma irradiation. The level of irradiation and
20 conditions of sterilization, including the time that the compositions are irradiated, are those that provide sterile compositions, as defined herein. Once having the benefit of this disclosure, one skilled in the art will be able to readily determine the level of irradiation necessary to provide sterile compositions.

As noted herein, thrombin, in an aqueous solution, has been found to lose all
25 procoagulant activity when exposed to sterilization irradiation. In contrast, sterile thrombin contained in compositions of the present invention retain enzymatic activity sufficient to provide hemostatic properties to compositions of the present invention after being subjected to irradiation sufficient to provide sterilized compositions disclosed herein. Sterile thrombin in compositions of the present invention may lose
30 only about 20 percent of its original enzymatic activity prior to sterilization. In certain embodiments of the present invention, the sterile thrombin exhibited a loss of enzymatic activity of not more than about 40% of its original enzymatic activity prior to

sterilization, while maintaining all of its hemostatic activity after sterilization, when formulated in compositions according to this invention. While bovine thrombin is exemplified herein, human-derived thrombin, as described in U.S. Patent No. 5,143,838, also may be used in compositions of the present invention. The discovery
5 that thrombin will maintain activity after being exposed to sterilizing radiation as described above is particularly surprising given the previous teachings of the art that would strongly suggest that if thrombin were to be used in hemostatic compositions it should be added after sterilization of the composition, not prior to sterilization.

The hemostatic compositions may further comprise effective amounts of one or
10 more additives or compounds including, but not limited to, antimicrobial agents, surfactants, antioxidants, humectants, wetting agents, lubricants, thickeners, diluents, irradiation stabilizers, e.g. radical scavengers, plasticizers, and stabilizers. For example, glycerol may be added to enhance the extrudability or injectability of the composition. When utilized, glycerol may be present in the compositions at from about
15 0% to about 20% by weight, based on the weight of the liquid phase. Preferably, the composition may comprise from about 1% to about 10% by weight of glycerol, based on the weight of the liquid phase. More preferably, the compositions may comprise from about 1% to about 5% by weight of glycerol, based on the weight of the liquid phase.

20 In addition, quaternary amines may be used to provide enhanced properties to the compositions. For example, benzalkonium chloride, Polybrene or Onamer M may be used at levels up to about 1 percent by weight, based on the weight of the liquid phase. Preferably, benzalkonium chloride is used at levels of from about 0.001% to about 0.01 % by weight, based on the weight of the liquid phase. More preferably, the
25 compositions may comprise from about 0.002 to about 0.006% by weight benzalkonium chloride, based on the weight of the liquid phase. It is believed that the quaternary amines may serve multiple functions, acting as an antimicrobial agent, a foaming agent, a radical scavenger and as a heparin neutralizer.

Such hemostatic compositions may further comprise heparin neutralizers,
30 additional procoagulants or hemostatic agents, such as fibrinogen, fibrin, Factor Xa, or Factor VIIa. By "effective amount", it is meant that amount necessary to provide to the compositions those properties for which the additive is being added. The effective

amount also is limited by the maximum amount that may be added without causing detrimental biological affects.

Medical devices in which the hemostatic compositions of the present invention may be utilized include any device currently being used to apply a flowable or
5 injectable hemostatic paste or slurry to a site, or wound, requiring hemostasis. The site requiring hemostasis may be the result of an injury or a surgical procedure. Examples of devices or applicators include syringes such as Becton Dickinson or Monoject luer syringes. Other devices are disclosed in detail in United States Patent No. 6,045,570, the contents of which are incorporated by reference in their entirety.

10 In one embodiment for making compositions of the invention, a substantially homogenous paste is prepared by mixing the particles with the liquid to form a uniform paste. The liquid includes the thrombin and may include effective amounts of other additives dissolved therein as described above. Mixing may be accomplished by extrusion or by mixing in a confined space under conditions effective to provide a
15 uniform dispersion of the solid particles in the liquid phase.

Alternately, a mixer, e.g. a double planetary mixer, may be utilized in making compositions of the present invention. The liquid containing the thrombin is added to the mixer. The liquid may include effective amounts of additives dissolved therein prior to addition of particles to the solution. For example, a saline solution containing
20 thrombin, glycerol and benzalkonium chloride may be prepared and then added to the mixer. The solid particles are added to the mixer over time with continuous mixing until all ingredients have been added. The mixing is continued until such time as a substantially homogenous composition is formed containing the solid particles uniformly dispersed throughout the continuous liquid phase.

25 The hemostatic compositions prepared as above are sterilized to provide sterile compositions comprising sterile thrombin. In some embodiments the compositions are transferred into a medical device as described above and the device containing the hemostatic composition is sterilized, preferably by ionizing radiation. More preferably, sterilization is by gamma irradiation as exemplified herein.

30 While the following examples demonstrate certain embodiments of the invention, they are not to be interpreted as limiting the scope of the invention, but rather as contributing to a complete description of the invention.

Example 1:

Two vials of lyophilized Bovine thrombin (20,000 units Thrombogen JJMI) were reconstituted in 20 ml of saline to provide a working solution of 1,000 units/ml.

5 Clotting activity was measured in an *in vitro* test as described in Example 2. One vial of this material was stored at 4-8°C and the clotting activity measured at day 1, day 8 and day 30, respectively. The second vial was sterilized by gamma irradiation (25kGy) and the clotting activity measured as above. The unsterilized and sterilized samples were designated samples 1a and 1b, respectively. Both sterilized and unsterilized

10 samples were stored at 4-8 °C between measurements.

Another 2 vials of 20,000 units of lyophilized bovine thrombin were reconstituted in saline containing 0.005% benzalkonium chloride and 5% glycerol. One vial was stored at 4-8°C and the clotting activity was measured at day 0, day 1, day 8 and day 30. The second vial was sterilized by gamma irradiation (25kGy) and the

15 clotting activity measured as above. In between measurements both the sterilized and unsterilized samples were stored at 4-8 °C. The unsterilized and sterilized samples were designated samples 1c and 1d, respectively.

Several samples of gelatin paste containing the thrombin noted above were prepared by mixing 1 gram of Surgifoam gelatin powder with 5 ml of thrombin

20 solution. The resulting paste was loaded into a 10cc syringe. Samples were then either sterilized at 25kGy followed by storage at 4-8°C, or stored unsterilized at 4-8°C. Samples so prepared are designated and identified below.

Sample 1e = 1 g Surgifoam® powder plus 5 ml of sample 1a; Sterilized

25 Sample 1f = 1 g Surgifoam® powder plus 5 ml of sample 1c; Unsterilized

Sample 1g = 1 g Surgifoam® powder plus 5 ml of sample 1c; Sterilized

Example 2:**Measurement of Thrombin activity by an *in vitro* coagulation test in a Fibrometer instrument (BBL)**

Method: Serial dilutions of test sample containing thrombin were prepared in Veronal buffer pH 7.2. 0.2 ml of pooled normal plasma (Citrol Level 1 control plasma-Dade Diagnostics) was warmed to 37°C in the fibrometer incubator block. 0.1 ml of pre-warmed sample dilution was added to the plasma and the timer started simultaneously. The time to clot formation was recorded. All samples were tested in duplicate and an average clotting time calculated. Data was graphed as the log₁₀ dilution vs. log₁₀ clotting time and a regression analysis performed. Freshly prepared thrombin was considered to have 100% activity and all other samples were calculated as a percentage of the activity relative to the freshly prepared thrombin. Results are presented in Table 1 and Table 2.

TABLE 1**Effect of Storage time on Thrombin Activity:****Stabilization by Formulated Gelatin Paste**

Storage Solution (Stored at 6°C)	Percent Loss in Thrombin Activity			
	Time 0	Day 1	Day 8	Day 30
1a	0	0	53.3	90.8
1c	0	NA	41.1	82.9
1f	0	0	0.8	0

TABLE 2**Effect of Gamma Irradiation on Thrombin Activity:****Stabilization by Formulated Gelatin paste**

Media for Sterilized Thrombin * Samples (5ml/g gelatin powder- 25 kGy Dose)	% Loss in Thrombin Activity
	Day 6
1b	100
1d	96.0
1e	72.6
1g	79.2

TABLE 3

In vivo Hemostasis Performance of Pre-filled Thrombin/Gelatin Paste

TIME: SAMPLE	Number of Compressions	Time to Hemostasis (mins:secs)
Day 0: 1f	1	0:30
Day 42: 1f	1	0:30
Day 42: 1f	1	0:30
Day 42: 1g	1	0:30
Day 42: 1g	1	0:30

5

Example 3: Sterilization of frozen Thrombin by Gelatin paste

One vial of 20,000 units of lyophilized bovine thrombin (Thrombogen JJMI) was reconstituted in saline containing 0.005% BAK and 5% glycerol. 1 gram of Surgifoam[®] powder was mixed with 5 ml of thrombin-containing saline solution . The

resulting paste was loaded into a 10 ml syringe. The sample were frozen at -20°C and sterilized by gamma irradiation at a dose of 25kG. Thrombin clotting activity was measures as described in Example 2. It was noted that only 42 percent of thrombin activity was lost due to sterilization.

5

10

We claim:

1. A sterile hemostatic composition, comprising:
a continuous, biocompatible liquid phase comprising sterile thrombin; and
a solid phase comprising particles of a biocompatible polymer suitable for use in
5 hemostasis and which is substantially insoluble in said liquid phase,
said continuous liquid phase comprising said solid phase and said sterile thrombin
substantially homogenously dispersed there through, wherein the ratio of said liquid
phase and said solid phase is effective to provide said composition with hemostatic
properties and said sterile thrombin comprises enzymatic activity.
10
2. The sterile hemostatic composition of claim 1 wherein said liquid phase
comprises saline.
3. The sterile hemostatic composition of claim 2 wherein said biocompatible
15 polymer is selected from the group consisting of proteins and polysaccharides.
4. The sterile hemostatic composition of claim 3 wherein said protein is selected
from the group consisting of gelatin, collagen, fibrinogen and fibronectin.
- 20 5. The sterile hemostatic composition of claim 4 wherein said protein comprises
gelatin.
6. The sterile hemostatic composition of claim 1 wherein said sterile thrombin has
lost not more than about 20 percent of the enzymatic activity it possessed prior to
25 sterilization.
7. The sterile hemostatic composition of claim 1 wherein said sterile thrombin has
lost not more than about 40 percent of the enzymatic activity it possessed prior to
sterilization.
30
8. A method for making a sterile hemostatic composition, comprising:
providing a biocompatible liquid having thrombin dissolved therein,

combining said liquid comprising said thrombin with particles of a biocompatible polymer suitable for use in hemostasis and which is substantially insoluble in said liquid,

5 mixing said liquid comprising said thrombin and said particles under conditions effective to form a continuous liquid phase comprising said thrombin and said particles substantially homogenously dispersed there through, thereby forming a substantially homogeneous hemostatic composition; and

10 irradiating said substantially homogeneous hemostatic composition with an amount of ionizing radiation and for a time effective to provide a sterile, substantially homogeneous hemostatic composition, wherein the ratio of said continuous liquid phase and said particles is effective to provide said composition with hemostatic properties and wherein said thrombin maintains at least a portion of its enzymatic activity.

15 9. The method of claim 8 wherein said liquid phase comprises saline.

10. The method of claim 9 wherein said biocompatible polymer is selected from the group consisting of proteins and polysaccharides.

20 10. The method of claim 9 wherein said protein is selected from the group consisting of gelatin, collagen, fibrinogen and fibronectin.

11. The method of claim 10 wherein said protein comprises gelatin.

25 12. The method of claim 8 wherein said sterile thrombin has lost not more than about 20 percent of the enzymatic activity it possessed prior to sterilization.

13. The method of claim 1 wherein said sterile thrombin has lost not more than about 20 percent of the enzymatic activity it possessed prior to sterilization.

30

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
24 February 2005 (24.02.2005)

PCT

(10) International Publication Number
WO 2005/016256 A3

(51) International Patent Classification⁷: A61K 38/48,
C12N 9/74, C12Q 1/56

(21) International Application Number:
PCT/US2004/023765

(22) International Filing Date: 23 July 2004 (23.07.2004)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
60/493,116 7 August 2003 (07.08.2003) US

(71) Applicant (for all designated States except US):
ETHICON, INC. [US/US]; U.S. Route #22, Somerville,
NJ 08876-1515 (US).

(71) Applicants and

(72) Inventors: PENDHARKAR, Sanyog, M. [US/US]; 9
Larch Drive, Old Bridge, NJ 08857 (US). GORMAN,
Anne, J. [US/US]; 314 Stockton Street, Hightstown, NJ
08520 (US).

(74) Agents: JOHNSON, Phillip et al.; Johnson & Johnson
Corporate, One Johnson & Johnson Plaza, New Brunswick,
NJ 08933-7003 (US).

(81) Designated States (unless otherwise indicated, for every
kind of national protection available): AE, AG, AL, AM,

AT, AU, AZ, BA, BB, BG, BR, BW, BY, BZ, CA, CH, CN,
CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, EG, ES, FI,
GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE,
KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD,
MG, MK, MN, MW, MX, MZ, NA, NI, NO, NZ, OM, PG,
PH, PL, PT, RO, RU, SC, SD, SE, SG, SK, SL, SY, TJ, TM,
TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM,
ZW.

(84) Designated States (unless otherwise indicated, for every
kind of regional protection available): ARIPO (BW, GH,
GM, KE, LS, MW, MZ, NA, SD, SL, SZ, TZ, UG, ZM,
ZW), Eurasian (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM),
European (AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI,
FR, GB, GR, HU, IE, IT, LU, MC, NL, PL, PT, RO, SE, SI,
SK, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ,
GW, ML, MR, NE, SN, TD, TG).

Published:

- with international search report
- before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

(88) Date of publication of the international search report:
15 September 2005

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: HEMOSTATIC COMPOSITIONS CONTAINING STERILE THROMBIN

(57) Abstract: The present invention includes sterilized hemostatic compositions that contain a continuous, biocompatible liquid phase having a solid phase of particles of a biocompatible polymer suitable for use in hemostasis and that is substantially insoluble in the liquid phase, and sterile thrombin, each of which is substantially homogeneously dispersed throughout the continuous liquid phase, and methods for making such compositions.



WO 2005/016256 A3

INTERNATIONAL SEARCH REPORT

International application No.

PCT/US04/23765

A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : A61K 38/48; C12N 9/74; C12Q 1/56

US CL : 424/94.64; 435/13, 214

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 424/94.64; 435/13, 214

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched
NONE

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)
WEST

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	US 2002/0042378 A1 (REICH et al) 11 April 2002 (11.04.2002), see the abstract and page 3, column 1, paragraph 0021, all lines and see pages 6-7, all lines.	1-13

☐ Further documents are listed in the continuation of Box C.

☐ See patent family annex.

Special categories of cited documents:

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T"

later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X"

document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y"

document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&"

document member of the same patent family

Date of the actual completion of the international search

21 March 2005 (21.03.2005)

Date of mailing of the international search report

12 JUL 2004

Name and mailing address of the ISA/US

Mail Stop PCT, Attn: ISA/US
Commissioner for Patents
P.O. Box 1450
Alexandria, Virginia 22313-1450

Facsimile No. (703) 305-3230

Authorized officer

Deborah K. Ware

Telephone No. 703-308-0196